

IN THE SPECIFICATION:

Kindly amend Tables 1, 4, and 5 as follows:

Table 1.

Battery No.	Capacity	Volts	Specific Gravity
1	150	5.9	LG
2	150	6.1	1140
3	150	5.7	1200
4	150	5.8	1180
5	150	5.5	1160
6	150	4.9	1200
7	150	5.0	1120
8	150	5.9	LG

Table 4

	Average Size of Lignin *	Specific Gravity	
		Before Charge	After Charge
Sample 1	0.3 mm	1.28	1.32
Sample 2	2.0 mm	1.24	1.30
Sample 3	no lignin	1.19	1.26

* micron

Table 5

	Average Size of Lignin *	150 Ampere 5-Second Test
		Voltage at 5 Seconds
Sample 1	0.3 mm	11.4 - 11.5 Volt
Sample 2	2.0 mm	11.1 - 11.2 Volt
Sample 3	no lignin	10.8 - 11.0 Volt

* micron